Powder Coating Technical Data Sheet

Date of first Issue: 08.02.2012 Revision date: 15.05.2012 Akzo Nobel Coatings CZ, a.s. Podvihovská 376/14 747 70 Opava 9 – Komárov Tel.: +420 553 692 275, Fax: +420 553 692 455 e-mail: czech@interpon.com • www.interpon.cz



Product range	Interpon 70	0				
Product name	ED352F					
Product Description	GREY white, Fine Texture, Matt					
Powder Properties	Chemical type	Epoxy – Polye	ster			
	Area of usage	General industrial, for interior use				
	Particle size distribution	n Custom manufactured				
	Density (g/cm ³)	$1,46 \pm 0,15$				
	Stoving schedule	10 min / 180 °C [Time at Object Temperature]				
	Application	Electrostatic (Corona)				
	Storage stability	Under dry, cool (< 30°C) conditions, at least 36 months from delivery date.				
	Safety Datasheet	PC010 (Mix	K-O)			
Coating Properties (Product Specification) Mechanical Tests:	Tests conditions	Test panel	Steel, thickness 0.6 ± 0.1 mm			
		Pre-treatment	Degreasing (event. phosphate - corrosion tests)			
		Film thickness	70 – 90 µm	ČSN EN I	SO 2808	
	Gloss (60°)	4 - 7	TP 101	(ČSN ISO 2813)		
	Adhesion (crosshatch)	GT 0	TP 96	(ČSN ISO 2409)		
	Erichsen cupping	min. 3 mm	TP 98	(ČSN EN ISO 1520)		
	Impact resistance	min. 30 cm	TP 100	100 (ČSN 67 3082 - Ø 12,9 mm, 0,5 kg)		
	Cylindrical flexibility	max. 5 mm	TP 99	(ČSN ISO	1519)	
Corrosion Tests	Salt Spray Test	240 h / Corrosion creep < 2 mm from scribe ČSN EN ISO 9227				
	Humidity Test	240 h / No blistering or loss of gloss ČSN EN ISO 6270-1				
Exterior Durability	Not intended for outdoor use.					
Chemical Durability	Generally good durability to most of common dilute acids, alkalis and oils at normal temperature.					
Safety Precautions	This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet which Akzo Nobel has provided to its customers.					
Disclaimer	The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage.					

