

## BU Powder Coatings

### Interpon 700 - EB2502 EE BIANCO 9010CA 25G

#### Product Description

**Interpon700** is a series of epoxy/polyester hybrid powder coatings offering improved colour, UV-light and heat stability compared to the **Interpon 100** range of pure epoxies, whilst maintaining an optimum combination of decorative and protective qualities.

**Interpon 700** powders are available in the full range of colours in gloss, reduced gloss, textured, aluminium and other special finishes or can be custom matched to the user's requirements.

#### Powder Properties

<b>Chemical type</b>	Epoxy/Polyester Hybrid
<b>Particle Size</b>	Suitable for electrostatic spray
<b>Specific gravity</b>	1.2 -1.7 g/cm <sup>3</sup> depending on color
<b>Storage</b>	Dry cool conditions below 35°C
<b>Shelf life</b>	24 months
<b>Sales Code</b>	E-series
<b>Stoving schedule<sup>(a)</sup></b> (object temperature)	20 minutes at 180°C 15 minutes at 190°C

(a) For full matt powders add 5 minutes to times shown.  
For high reactivity powders see overleaf

#### Test Conditions

The results shown below are based on mechanical and chemical tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for guidance only. Actual product performance will depend upon the circumstances under which the product is used.

<b>Substrate</b>	Mechanical tests: Polished steel Chemical & durability tests: Pre-treated steel
<b>Pretreatment</b>	Zinc phosphate (or equivalent pre-treatment)
<b>Film Thickness</b>	60 microns
<b>Stoving</b>	15 minutes at 190°C (object temperature)

#### Mechanical Tests

<b>Flexibility</b>	ISO 1519:73 (cylindrical mandrel)	Pass 5mm
<b>Adhesion</b>	ISO 2409-1992 (2 mm crosshatch)	GT0
<b>Erichsen cupping</b>	ISO 1520	Pass >6mm
<b>Hardness</b>	ISO 15184 (2000gr)	Pass H – 2H
<b>Impact</b>	ISO 6272:1993	Pass 3 Joule D/R

#### Chemical and Durability Tests

<b>Salt Spray</b>	ISO7253 (500 hours)	Pass - no corrosion creep more than 3mm from scribe
<b>Cyclic Humidity</b>	ISO 6720-1:1998 (1000 hours)	Pass - no blistering or loss of gloss
<b>Distilled Water Immersion</b>	ISO 2812-2:1993 (240 hours)	Pass - no blistering or loss of gloss
<b>Exterior Durability</b>	Some chalking after 6-12 months continuous outdoor exposure. Protective properties not impaired	
<b>Colour Stability at elevated temperatures</b>	Good - satisfactory for continuous exposure up to 100°C	
<b>Chemical Resistance</b>	Generally good resistance to acids, alkalis and chemical substances at room temperatures	

## Interpon 700

---

<b>Pretreatment</b>	Aluminium, steel or Zintec surfaces to be coated must be clean and free from grease. Iron phosphate and particularly lightweight zinc phosphating (or equivalent pre-treatment) of ferrous metals improves corrosion resistance. Aluminium substrates may require a chromate conversion coating (or equivalent pre-treatment)
<b>Application</b>	<b>Interpon 700</b> powders can be applied by manual or automatic electrostatic spray equipment. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.
<b>Applications in the marine field</b>	For marine applications, related to cycles approved RINA /MED, the thickness of the metal support must be $> = 0.6\text{mm}$ , and the thickness of the coating film must respect the value of $80\mu \pm 10\%$

---

### Additional Informations

**Interpon 700** powders are available in bright aluminium finishes which are susceptible to scratching and finger marking. Protection by use of a clear polyester top coat is recommended when the coated article is to be subjected to physical damage or environmental damage. The top coat should ideally be applied within 2 hours of the metallic coating and gloves should be worn when handling the metallic coated articles.  
For further details on the use of metallic powder coatings please contact Akzo Nobel.

**Interpon 700HR** (High Reactivity) powders are also available for use where a lower stoving temperature or shorter curing schedule is required.

**Sales code:** F-Series

**Stoving schedule:** 15 minutes at 160°C

(object temperature) 5 minutes at 180°C

**Shelf life:** 12 months

For further details on powder properties and film performance of **Interpon 700HR** please contact Akzo Nobel.

---

**Safety Precautions** Please consult the Material Safety Datasheet (MSDS)

---

### FOR PROFESSIONAL USE ONLY

---

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel

Akzo Nobel Coatings Spa – Via Silvio Pellico, 8 – 22100 Como - Italy  
Tel: ++39.031.345 111 - Fax: ++39.031.345 352 - [WWW.interpon.com](http://WWW.interpon.com)  
Interpon is a trademark of Akzo Nobel group